

ExxonMobil™ LLDPE LL 3003 Series

Linear Low Density Polyethylene Resin

Product Description

ExxonMobil™ LL 3003 Series are ethylene 1-hexene copolymer linear low density polyethylene cast film resins. Films made from LL 3003 resins have outstanding tensile properties, as well as stiffness and toughness. These superior properties, along with excellent drawability, make LL 3003 versatile packaging film resins.

General

Availability ¹	▪ Latin America	▪ North America
Additive	▪ LL 3003.39: Antiblock: No; Slip: No; Processing Aid: No; Thermal Stabilizer: Yes ▪ LL 3003.32: Antiblock: No; Slip: No; Processing Aid: No; Thermal Stabilizer: Yes	
Applications	▪ Cast Film	▪ Cast Stretch Film
Form(s)	▪ Pellets	
Revision Date	▪ 06/11/2020	

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density / Specific Gravity	0.918 g/cm ³	0.918 g/cm ³	ASTM D792
Melt Index (190°C/2.16 kg)	3.2 g/10 min	3.2 g/10 min	ASTM D1238
Peak Melting Temperature	255 °F	124 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	199 °F	93.0 °C	ExxonMobil Method

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield MD	1300 psi	8.7 MPa	ASTM D882
Tensile Strength at Yield TD	1200 psi	8.2 MPa	ASTM D882
Tensile Strength at Break MD	6900 psi	47 MPa	ASTM D882
Tensile Strength at Break TD	4700 psi	33 MPa	ASTM D882
Elongation at Break MD	510 %	510 %	ASTM D882
Elongation at Break TD	820 %	820 %	ASTM D882
Secant Modulus MD - 1% Secant	19000 psi	130 MPa	ASTM D882
Secant Modulus TD - 1% Secant	21000 psi	150 MPa	ASTM D882
Dart Drop Impact	100 g	100 g	ASTM D1709A
Elmendorf Tear Strength MD	170 g	170 g	ASTM D1922
Elmendorf Tear Strength TD	580 g	580 g	ASTM D1922
Puncture Force	7 lbf	32 N	ExxonMobil Method
Puncture Energy	23 in-lb	2.6 J	ExxonMobil Method

Optical Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Gloss (45°)	91	91	ASTM D2457
Haze	2.0 %	2.0 %	ASTM D1003

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

Film (0.8 mil / 20 micron) made from LL 3003.32 resin on a 3.5 inch cast film line with a 8.25 inch melt curtain, 80°F (27°C) chill roll temperature at a 400 ft/min (122 m/min) take-off speed and a melt temperature of 530°F (277°C).

ExxonMobil™ LLDPE LL 3003 Series
Linear Low Density Polyethylene Resin

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2024 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com