

# SABIC® HDPE B5628

## TECHNICAL DATA SHEET HIGH DENSITY POLYETHYLENE

### DESCRIPTION

HDPE B5628 is a High Density Polyethylene specially developed for small blow molded bottles. The material offers easy flow, higher stiffness, good combination of ESCR and sufficient impact strength.

### TYPICAL APPLICATIONS

B5628 is specially designed for: - Industrial Chemicals & Parts - Bleach and Detergents - Personal Care Products  
This product is not intended for and must not be used in any pharmaceutical/medical applications.

### TYPICAL PROPERTY VALUES

Revision 20240326

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES <sup>(1)</sup></b>			
<b>Melt Flow Rate (MFR)</b>			
@ 190°C & 21.6 kg load	24	g/10 min	ASTM D1238
@ 190°C & 2.16 kg load	0.32	g/10 min	ASTM D1238
<b>Density</b>			
@23°C	955	kg/m <sup>3</sup>	ASTM D1505
<b>MECHANICAL PROPERTIES <sup>(2)</sup></b>			
<b>Tensile Properties</b>			
Tensile Strength at Yield, 500mm/min, Type IV bar	30	MPa	ASTM D638
<b>Tensile Elongation</b>			
@ Break, 10mm/min, Type IV bar	> 903	%	ASTM D638
<b>Flexural Modulus</b>			
Tangent - 16:1 span:depth, 0.5 in/min	1120	MPa	ASTM D790
<b>Izod Impact @ 23oC</b>			
	148	J/m	ASTM D256
<b>Durometer Hardness</b>			
(Shore D)	58	-	ASTM D2240
<b>THERMAL PROPERTIES <sup>(2)</sup></b>			
<b>Vicat softening temperature</b>			
Loading 1, Rate A	127	°C	ASTM D1525
<b>Heat deflection temperature</b>			
66 psi, Method A	70	°C	ASTM D648

(1) Typical values: not to be construed as specification limits.

(2) Based on compression molded specimens.

### PROCESSING CONDITIONS

Recommended processing temperatures: 190 - 230°C

### HEALTH AND SAFETY CONSIDERATIONS AND PRECAUTIONS

Detailed information is provided in the relevant Material Safety Datasheet and or Standard Food Declaration, Additional specific information can be requested via your local Sales Office.

© 2024 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



## STORAGE AND HANDLING

Polyethylene material should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions, which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.