

SABIC® LLDPE 926NT

LINEAR LOW DENSITY POLYETHYLENE
REGION ASIA

DESCRIPTION

SABIC® 926NT is an ethylene-butene copolymer designed for blown film application. Excellent mechanical strength, tear and puncture resistance, 926NT contains no slip and no antiblock.

TYPICAL APPLICATIONS

Heavy duty film, agriculture film, general purpose packaging film, stretch film, carrier bag, produce bag, etc.

TYPICAL PROPERTY VALUES

Revision 20201209

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 190°C and 2.16 kg	0.85	g/10 min	ASTM D1238
Density at 23°C	926	kg/m ³	ASTM D1505
MECHANICAL PROPERTIES			
Tensile test			
stress at yield, MD	12	MPa	ASTM D882
stress at yield, TD	10	MPa	ASTM D882
stress at break, MD	36	MPa	ASTM D882
stress at break, TD	29	MPa	ASTM D882
elongation at break, MD	550	%	ASTM D882
elongation at break, TD	600	%	ASTM D882
OPTICAL PROPERTIES			
Gloss			
at 45°	60	-	ASTM D2457
Haze ⁽¹⁾	14	%	ASTM D1003
FILM PROPERTIES			
Dart Impact F50	90	g	ASTM D1709
Tear Resistance			
MD	35	g	ASTM D1709
TD	135	g	ASTM D1709
Puncture resistance	70	J/m	SABIC method

(1) Properties have been measured by producing 30 μ film with 2.0 BUR using 100% 926NT.

PROCESSING CONDITIONS

Typical processing conditions for 926NT are:

Barrel temperature: 190 - 220°C

Blow up ratio: 2.0 - 3.0



STORAGE AND HANDLING

Polyethylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.