

# SABIC® LLDPE P118

LINEAR LOW DENSITY POLYETHYLENE FOR PIPES

## DESCRIPTION

P118 is a natural linear low density polyethylene (LLDPE) resin, designed for non-pressure pipe extrusion application.

## TYPICAL APPLICATIONS

The grade is designed to be used as blend with HDPE for Non-Pressure pipe applications such as irrigation, cable conduits, corrugated & gravity pipe segments.

## TYPICAL PROPERTY VALUES

Revision 20240709

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES <sup>(1)</sup></b>			
<b>Melt Flow Rate (MFR)</b>			
@ 190°C & 2.16kg load	1	g/10 min	ASTM D1238
@ 190°C & 5 kg load	3.3	g/10 min	ASTM D1238
<b>Density</b>			
Density at 23°C	918	kg/m <sup>3</sup>	ASTM D792
<b>MECHANICAL PROPERTIES <sup>(1)</sup></b>			
<b>Tensile strength</b>			
Tensile @ Yield <sup>(2)</sup>	10.9	MPa	ASTM D638
Tensile @ Break	15.4	MPa	ASTM D638
Elongation @ Yield	17.2	%	ASTM D638
Elongation @ Break	574	%	ASTM D638
Tensile Modulus	345	MPa	ASTM D638
Flexural Modulus	173.4	MPa	ASTM D790
<b>Hardness</b>			
Hardness (shore D) <sup>(3)</sup>	42.4	-	ASTM D2240
<b>THERMAL PROPERTIES</b>			
<b>Vicat Softening Temperature</b>			
Vicat	102.5	°C	ASTM D1525

(1) Typical values; not to be construed as specification limits

(2) Test specimen, thickness 3.2 mm with 50mm/min test speed

(3) Based on injection molded sheet

## STORAGE AND HANDLING

Polyethylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process polyethylene resin within 6 months after delivery.



## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.