

# SABIC® PP 510P

POLYPROPYLENE HOMOPOLYMER

## DESCRIPTION

SABIC® PP 510P is a fibre grade with an anti gas fading stabilisation package. This grade is suitable for e.g. wipes and industrial carpets.

## TYPICAL APPLICATIONS

SABIC® PP 510P is suitable for spinning of coarse staple fibres, carpet fibres, yarns and geotextiles with moderate tenacity. It can be also used for the production of continuous filament.

## TYPICAL PROPERTY VALUES

Revision 20201214

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate (MFR)</b>			
at 230 °C and 2.16 kg	12	dg/min	ISO 1133
<b>Density</b>	905	kg/m <sup>3</sup>	ASTM D1505
<b>Molecular Weight Distribution</b>	Broad	-	-
<b>Isotacticity</b>	Medium	-	-
<b>FORMULATION</b>			
<b>Anti block agent</b>	<input type="checkbox"/>	-	-
<b>Slip agent</b>	<input type="checkbox"/>	-	-
<b>Anti static agent</b>	<input type="checkbox"/>	-	-
<b>Nucleating agent</b>	<input type="checkbox"/>	-	-
<b>Gas fading stabilized</b>	<input checked="" type="checkbox"/>	-	SABIC method
<b>MECHANICAL PROPERTIES</b>			
<b>Tensile test</b>			
strain at break	600	%	ISO 527
tensile modulus <sup>(1)</sup>	1700	MPa	ISO 527-2 1A
strain at yield <sup>(2)</sup>	11	%	ISO 527-2 1A
stress at break	-	MPa	ISO 527
stress at yield	35	MPa	ISO 527-2 1A
<b>Flexural test</b>			
Flexural modulus	1700	MPa	ASTM D790
<b>THERMAL PROPERTIES</b>			
<b>Vicat Softening Temperature</b>			
at 50 N (VST/B)	82	°C	ISO 306/B
at 10 N (VST/A)	153	°C	ISO 306/A

(1) Speed of testing: 1 mm/min

(2) Speed of testing: 50 mm/min

## PROCESSING CONDITIONS

Typical processing conditions for 510P are:

Average extrusion temperature range may be kept at 210 - 240°C.

## STORAGE AND HANDLING

Polypropylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PP resin within 6 months after delivery.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.