

SABIC® PP 513A

PP HOMOPOLYMER

DESCRIPTION

SABIC® PP 513A is a fibre grade with an anti gas fading stabiliser package. Application: SABIC® PP 513A is typically used by our customer for extrusion of staple fibres used in geo-textile applications with an optimum balance of tenacity/elongation.

Health, Safety and Food Contact regulations: Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC.com>.

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

This grade material is UL registered under File E111275 (www.ul.com)
IMDS 7172624

TYPICAL PROPERTY VALUES

Revision 20220218

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 230 °C and 2.16 kg	5.8	dg/min	ISO 1133
Density	905	kg/m ³	ASTM D1505
Molecular Weight Distribution	Broad	-	-
Isotacticity	Medium	-	-
FORMULATION			
Gas fading stabilized	<input checked="" type="checkbox"/>	-	SABIC method
MECHANICAL PROPERTIES			
Tensile test			
strain at yield ⁽¹⁾	8	%	ISO 527-2 1A
tensile modulus ⁽²⁾	1700	MPa	ISO 527-2 1A
stress at yield	37	MPa	ISO 527-2 1A

(1) Speed of testing: 50 mm/min

(2) Speed of testing: 1 mm/min

STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.