

SABIC® PP 5212P

POLYPROPYLENE HOMOPOLYMER

DESCRIPTION

PP 5212P is high stiffness PP Homopolymer grade, specially developed for bi-axially oriented PP (BOPP) film extrusion with a very specific molecular structure providing ultimate properties required for the stenter film process. Films produced using PP 5212P will exhibit:

- Good process ability, Good thickness control
- Good optical properties
- High tensile properties & High stiffness
- Low residual ash
- Film produced can be metalized

TYPICAL APPLICATIONS

PP 5212P can be used as core layer in co-extruded film and/or as base material for plain films used for label film, stationary, dry food bags, synthetic paper and heat sealable packaging films.

TYPICAL PROPERTY VALUES

Revision 20211207

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES ⁽¹⁾			
Melt Flow Rate (MFR)			
@ 230°C/2.16 kg	3	g/10 min	ASTM D1238
Density	905	kg/m ³	ASTM D792
MECHANICAL PROPERTIES ⁽²⁾			
Tensile Strength at Yield	36	MPa	ASTM D638
Tensile Elongation at Yield	10	%	ASTM D638
Flexural Modulus (1% Secant)	1800	MPa	ASTM D790 A
Notched Izod Impact Strength at 23°C	46	J/m	ASTM D256
Rockwell Hardness, R-Scale	102	-	ASTM D785
THERMAL PROPERTIES			
Vicat Softening Point	>154	°C	ASTM D1525
Heat Deflection Temperature at 455kPa	110	°C	ASTM D648
Crystallization Temperature (T_c)	123	°C	ASTM D3418

(1) Typical values; not to be construed as specification limits.

(2) Based on injection molded specimens

PROCESSING CONDITIONS

Average extrusion temperature range may be kept at 240 - 250°C

HAZARDS AND SAFETY

PP 5212P is suitable for Food contact application. Detailed information is provided in relevant Material Safety Datasheet and for additional specific information please contact SABIC local representative for certificate.

DISCLAIMER: This product is not intended for and must not be used in any pharmaceutical/medical applications.



STORAGE AND HANDLING

Polypropylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PP resin within 6 months after delivery.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.