

SABIC® PP 5232P

PROVISIONAL DATA SHEET POLYPROPYLENE HOMOPOLYMER

DESCRIPTION

SABIC® PP 5232P is a polypropylene homopolymer designed for production of biaxially oriented polypropylene films (BOPP). It offers good optical properties and ease processing, and recommended to be used as mono and co-extruded layer structure for metalizable films.

TYPICAL APPLICATIONS

SABIC® PP 5232P can be used for Biaxially Oriented Polypropylene (BOPP) packaging film and thermoforming sheets. SABIC® PP 5232P can be used as core layer in co-extruded film and/or as base material for plain films used for label film, stationary, dry food bags, synthetic paper and heat sealable packaging films.

TYPICAL PROPERTY VALUES

Revision 20230511

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES ⁽¹⁾			
Melt Flow Rate (MFR)			
at 230°C and 2.16kg	3	g/10 min	ISO 1133
MECHANICAL PROPERTIES ⁽²⁾			
Tensile Strength at Yield	35	MPa	ISO 527-2
Flexural Modulus	1400	MPa	ISO 178/1A
Izod Impact , Notched, 23 °C	4.5	kJ/m ²	ISO 180

(1) Typical values, not to be construed as specific limits.

(2) Based on injection molded specimens

PROCESSING CONDITIONS

Typical processing conditions for 5232P are:

Average extrusion temperature range may be kept at 240 - 250°C

STORAGE AND HANDLING

Polypropylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PP resin within 6 months after delivery.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.