

# SABIC® PP 525P

## PP HOMOPOLYMER

### DESCRIPTION

SABIC® PP 525P is particularly developed for (biaxially) oriented PP film extrusion with a very specific molecular structure providing the ultimate properties required for the stretching process.

Application: SABIC® PP 525P is typically used in mono layer or coextruded (B)OPP film. SABIC® PP 525P is known for its excellent metallisation behaviour.

Health, Safety and Food Contact regulations:

SABIC® PP 525P has a Food Contact Declaration. Material Safety Data Sheets (MSDS) and Product Safety Declarations are available on our Internet site <http://www.sabic.com>.

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

This grade material is UL registered under File E111275 ([www.ul.com](http://www.ul.com))  
IMDS 7172624

### TYPICAL PROPERTY VALUES

Revision 20210702

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate (MFR)</b>			
at 230 °C and 2.16 kg	3.0	dg/min	ISO 1133
<b>Density</b>	905	kg/m <sup>3</sup>	ASTM D1505
<b>Molecular Weight Distribution</b>	Broad	-	-
<b>Isotacticity</b>	Medium	-	-
<b>FORMULATION</b>			
<b>Anti block agent</b>	<input type="checkbox"/>	-	-
<b>Slip agent</b>	<input type="checkbox"/>	-	-
<b>Anti static agent</b>	<input type="checkbox"/>	-	-
<b>Nucleating agent</b>	<input type="checkbox"/>	-	-
<b>MECHANICAL PROPERTIES</b>			
<b>Tensile test</b>			
strain at yield	10	%	ISO 527-2 1A
tensile modulus <sup>(1)</sup>	1550	MPa	ISO 527-2 1A
stress at yield <sup>(2)</sup>	37	MPa	ISO 527-2 1A
<b>Izod impact notched</b>			
at 23 °C	3.5	kJ/m <sup>2</sup>	ISO 180/1A
<b>Charpy Impact Strength Notched</b>			
at 23 °C	4.5	kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL PROPERTIES</b>			
<b>Heat deflection temperature <sup>(3)</sup></b>			
at 0.45 MPa (HDT/B)	85	°C	ISO 75
at 1.80 MPa (HDT/A)	55	°C	ISO 75
<b>Vicat Softening Temperature <sup>(4)</sup></b>			
at 10 N (VST/A)	152	°C	ISO 306
at 50 N (VST/B)	88	°C	ISO 306

- (1) Speed of testing: 1 mm/min
- (2) Speed of testing: 50 mm/min
- (3) Flat wise ( testbar 80\*10\*4mm)
- (4) Temperature rate: 120°C/h

## STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.