

SABIC® PP BCT18F

PP IMPACT COPOLYMER - PROVISIONAL DATASHEET

DESCRIPTION

A phthalate free and gel controlled film grade that provides excellent impact resistance at low temperature, retort ability and sealing properties. The balanced viscosity characteristics making this grade suitable for the main film processing technologies (blown, cast, tenter frame biaxial orientation). This grade can also be made available as TRUCIRCLE™ certified renewable or certified circular polymer.

TYPICAL PROPERTY VALUES

Revision 20220728

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 230 °C and 2.16 kg	1.8	dg/min	ISO 1133
Density	905	kg/m ³	ASTM D1505
OPTICAL PROPERTIES			
Haze ⁽¹⁾	89	%	ASTM D1003
Gloss			
45°	4	%	ASTM D2457
FILM PROPERTIES			
Tensile test film			
Tensile strength at yield MD ⁽¹⁾	15	MPa	ASTM D882
Tensile Strength at yield TD ⁽¹⁾	15	MPa	ASTM D882
Elongation at yield MD ⁽¹⁾	7	%	ASTM D882
Elongation at yield TD ⁽¹⁾	6	%	ASTM B822
Tensile Modulus MD ⁽¹⁾	638	MPa	ASTM D882
Tensile Modulus TD ⁽¹⁾	563	MPa	ASTM B822
Sealing Initiation Temperature ⁽¹⁾	145	°C	SABIC method

(1) on 25µm thick film produced with SABIC internal standard conditions on cast technology.

STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.