

Technical Data Sheet

Typical Applications

- Used for the production of thin-walled articles, containers, toys, vacuum flasks, household and kitchen articles
- Components of compounding and master batches application
- Lamination application

Key Characteristics

- High fluidity
- High stiffness
- Outstanding processability
- Easy mold filling
- Short cycle times
- Good dimensional stability
- Food contact approval for specific applications (refer to *NATPET*)

Processing Methods

- Injection Molding
- Sheet lamination

| Resin | Conditions | Method | Value | Unit |
|-----------------------------|----------------------|----------------|-------|-------------------|
| Density | 23 °C | ISO 1183 | 0.900 | g/cm ³ |
| Melt Flow Rate (MFR) | 230 °C/2.16 kg | ASTM D 1238-13 | 25 | g/10-min |
| Mechanical | | | | |
| Flexural Modulus | | ISO 178 | 1,500 | MPa |
| Tensile Stress at Break | 50-mm/min | ISO 527 | 23 | MPa |
| Tensile Stress at Yield | 50-mm/min | ISO 527 | 32 | MPa |
| Tensile Strain at Break | 50-mm/min | ISO 527 | > 50 | % |
| Tensile Strain at Yield | 50-mm/min | ISO 527 | 13 | % |
| Izod <small>Notched</small> | 23 °C | ISO 180 | 4.1 | kJ/m ² |
| Thermal | | | | |
| Heat Deflection Temperature | 0.45 MPa Un-annealed | ISO 75B | 94 | °C |
| Vicat Softening Temperature | A50 (50 °C/h 10N) | ISO 306 | 152 | °C |

Technical information

Note: The above are typical data representing the product; not to be construed as analysis certificate or specifications.

DS v3.1

For further details about *NATPET* and its products, please visit the website at www.natpet.com

NATPET® products, marketed under the trade name Teldene®, are intended for the use by those customers and/or any other consumers, who undertake to become responsible to independently establish on their own the appropriateness of the product for its intended use, covering all safety and legally enacted requirements at the location of its projected use and the legal disposal practices thereof. The description of the product as given in this sheet shall under no circumstances be construed as warranty, express or implied including a warranty of merchandize fitness for a particular purpose. On behalf of *NATPET*, no one is authorized to make any such warranties, or take up on their own to assume such a liability. In case of product related claims, the sole and maximum remedy will be the physical substitution of the product or reimbursement of the purchase value, as per *NATPET*'s options. Further claims based on consequential, secondary, castigatory, or extraordinary damages will in no way entertained by *NATPET*.
NATPET would like to advise its customers and other users that unless specifically stated the supplied products should not be used for applications in medical and/or pharmaceutical sectors.

Technical Data Sheet

Special Features

Shows broad processing window while providing good mechanical properties

Processing Conditions

Average extruder temperature range may be kept between 220 - 240 °C.

Food Regulation

This product is defined as a preparation under specific food contact regulation. Detailed information will be provided in a relevant document "Regulatory Compliances Product Declaration" upon request.

Storage and Handling

Polypropylene resin should be stored to prevent a direct exposure to sunlight and heat. The Product estimated shelf life is one year starting from production date, adequate humidity below 80%, and temperature below 40 °C. Customers might not fully follow the optimal storage condition, hence the shelf life recommended at customer site is six months only as received. Please refer to "Material Safety Datasheet" (MSDS) for handling and storage information.

Documents

Specific documents MSDS and RCPD are available on request. Please send your request to the following e-mail: pa@natpet.com or visit our website : WWW.natpet.com