

## Marlex<sup>®</sup> D143FK Polyethylene

### METALLOCENE LINEAR LOW DENSITY POLYETHYLENE (mLLDPE)

**This metallocene linear low density polyethylene is an ethylene-hexene copolymer tailored for blown film applications that require:**

- Superb clarity
- Excellent gloss
- Exceptional toughness
- Outstanding heat seal

**Typical blown film applications include:**

- Seal layer in coextrusions
- Heavy duty packaging
- Clarity packaging

Nominal Resin Properties	English	SI	Method
Melt Index, 190 °C/2.16 kg	---	1.4 g/10 min	ASTM D1238
Density	---	0.916 g/cm <sup>3</sup>	ASTM D1505
Slip	1000 ppm	1000 ppm	---
Antiblock	5000 ppm	5000 ppm	---
Process Aid	Yes	Yes	---

Nominal Blown Film Properties at 1 mil <sup>1</sup>	English	SI	Method
Haze	9 %	9 %	ASTM D1003
Gloss, 60°	105	105	ASTM D2457
COF	0.15	0.15	ASTM D1894
Dart	---	580 g/mil	ASTM D1709
Elmendorf Tear MD/TD	---	170 g/mil	ASTM D1922
Elmendorf Tear MD/TD	---	370 g/mil	ASTM D1922
Tensile Strength at Yield MD/TD	1800 psi	12 MPa	ASTM D882
Tensile Strength at Yield MD/TD	1400 psi	10 MPa	ASTM D882
Tensile Strength at Break MD/TD	7500 psi	52 MPa	ASTM D882
Tensile Strength at Break MD/TD	6450 psi	44 MPa	ASTM D882
Tensile Elongation at Break MD/TD	450 %	450 %	ASTM D882
Tensile Elongation at Break MD/TD	550 %	550 %	ASTM D882
1 % Secant Modulus MD/TD	22000 psi	152 MPa	ASTM D882
1 % Secant Modulus MD/TD	22700 psi	157 MPa	ASTM D882
Seal Initiation Temperature <sup>2</sup>	216 °F	102 °C	ASTM F88

1. Produced on a LLDPE line at 2.5:1 BUR, 80 mil die gap, 8 in die, 250 lb/h, 400 °F melt temperature.

2. Temperature at which 0.3 lb/in heat seal strength is achieved. 0.5 s dwell, 30 psi pressure, 11.8 in/min separation rate.

Revision Date: October, 2021



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.