

Luban EP2340P

Polypropylene Impact Copolymer



Description

Luban EP2340P is manufactured using the Spheripol Technology. Luban EP2340P is a nucleated impact copolymer polypropylene, suitable for injection molding applications. It exhibits a high stiffness combined with a good impact balance. The grade is recommended to be used in luggage, battery cases, houseware items, containers, caps and closures.

Application

Houseware, luggage, pails, containers, caps & closures, automotive battery cases.

Properties (Typical Values)

| Property | Units | Test method | Value |
|-------------------------------------|--------------------|-------------|-------|
| Melt flow rate (230°C/2.16 kg) | g/10 min | ISO 1133 | 15 |
| Density | g /cm ³ | ISO 1183 | 0.90 |
| Tensile modulus (1 mm/min) | MPa | ISO 527 | 1350 |
| Tensile stress at yield (50 mm/min) | MPa | ISO 527 | 27 |
| Elongation at Yield | % | ISO 527 | 6 |
| Tensile Stress at Break (50 mm/min) | MPa | ISO 527 | 18 |
| Elongation at Break | % | ISO 527 | >100 |
| Notched Charpy Impact (+ 23°C) | kJ/m ² | ISO 179 | 7.0 |
| Notched Charpy Impact (0°C) | kJ/m ² | ISO 179 | 3.7 |
| Notched Charpy Impact (-20°C) | kJ/m ² | ISO 179 | 3.0 |
| Vicat Softening Point (10N) | °C | ISO 306/A | 152 |
| Heat Deflection Temperature | °C | ISO 75 | 96 |

Note: These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

Processing Guidelines

The Typical Processing Conditions for Luban EP2340P are:

| | |
|-------------------------|--|
| Melt temperature | 220 – 260 °C |
| Holding pressure | 200 – 500 bar Maximum to avoid sink marks |
| Mold temperature | 20 – 40 °C |
| Injection speed | High |
| Shrinkage | 1 – 2 % depending on wall thickness and molding parameters |

Luban EP2340P

Polypropylene Impact Copolymer



Note: Processing parameters should only be used as guidelines. The above properties values are not to be construed as specifications.

Storage and Handling

Luban EP2340P must be protected from direct sunlight and should be stored in a shaded and completely dry area. During handling and processing, the material should be kept in a well-ventilated area to prevent the accumulation of dust and fumes. Contact with strong oxidizers, excessive heat, sparks or open flame should be avoided as this could initiate the degradation process and consequently impact the quality of the material.

Safety

Luban EP2340P is not classified as dangerous preparation. For further information about safety in handling and processing please refer to the Safety Data Sheet.

Food Contact

Luban EP2340P meets the requirements of the U.S. Food and Drug Administration (FDA) as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact. For additional information on approved conditions of use for food contact applications, please refer to the "Product Stewardship Declaration".

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Updated: March. 2023

Disclaimer:

Values given here are typical and should not be interpreted as specification. Before using OQ product, customers and other users should make their own independent determination that the product is suitable for the intended use. This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. In addition, no immunity under OQ or third parties' intellectual property rights shall be implied from this document. No one is authorized to make any warranties, issue any immunities or assume any liabilities on behalf of OQ except in a writing signed by an authorized OQ employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at OQ's option, and in no event shall OQ be liable for special, consequential, incidental, punitive or exemplary damages.