

PRODUCT DATA SHEET

POLYPROPYLENE

Daplen™ EE158AIC

ELASTOMER MODIFIED 10% MINERAL FILLED POLYPROPYLENE FOR INJECTION MOLDING

DESCRIPTION

Daplen EE158AIC is an elastomer modified 10% mineral filled polypropylene compound for injection molding. It shows excellent mechanical properties high stiffness and impact strength and contains a UV stabilization package for interior application.

APPLICATIONS

Daplen EE158AIC is designed for automotive interior parts

Door Panels	Interior Trims
Pillars	Dashboards

PHYSICAL PROPERTIES

Property	Typical Value	Test Method
Density	980 kg/m ³	ISO 1183
Melt Flow Rate (230°C/2.16kg)	12 g/10min	ISO 1133
Flexural Modulus (2mm/min)	1550 MPa	ISO 178
Tensile Stress at Yield (50mm/min)	20 MPa	ISO 527-2
Heat Deflection Temperature B (0.45 N/mm ²)	95 °C	ISO 75-2
Charpy Impact Strength, notched (23°C)	25 kJ/m ²	ISO 179/1eA
Fogging Gravimetric (100°C, 16h)	<2.0 mg	DIN 75201
Emissions	<50 µgC/g	VDA 277
Mould Average Shrinkage*	1.1% - 1.3%	Borouge Method

*Measured on 150 mm x 90 mm x 3 mm plaques at conditions 23°C. These values are only valid as a reference and not for specification/tool cutting purpose.

*Data should not be used for specification work

PROCESSING CONDITIONS

The actual conditions will depend on the type of equipment used.

This product is easy to process with standard injection moulding machines. To avoid residual humidity from transport or storage, the material should be pre-dried approximately 2h at 80°C.

Following parameters should be used as guidelines:

Holding pressure	50% - 70% of the injection pressure
Mould temperature	30 - 50°C
Injection mass temperature	220 - 260°C
Injection speed	Low to medium

Screw speed

Slow to medium

Specific recommendations for processing conditions can be determined only when the application and type of equipment are known. Please contact your local Borouge representative for such particulars.

STORAGE

Daplen EE158AIC should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage can be found in Safety Information Sheet (SIS) for this product.

SAFETY

The product is not classified as a hazardous preparation.

Please see our Safety Information Sheet (SIS) for details on various aspects of safety, recovery and disposal of the product, for more information contact your Borouge representative.

RECYCLING

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

RELATED DOCUMENTS

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

Safety Information Sheet
Statement on chemicals, regulations and standards

STANDARDS

Borouge is certified to various ISO standards, please refer to Borouge.com for more information.

DISCLAIMER

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borouge makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose.

The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of Borouge products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

Edition 3, April 2018