

PRODUCT DATA SHEET

POLYETHYLENE

Borstar® FB1200

ENHANCED ETHYLENE - ALPHA - OLEFINS COPOLYMER FOR HIGH PERFORMANCE AGRICULTURE FILM APPLICATIONS

DESCRIPTION

Borstar®FB1200 is produced using the proprietary **Borstar®** bimodal technology resulting in easy extrusion with superior mechanical properties. Film made from the product exhibits excellent mechanical strength at normal as well as low temperature, good sealing properties and superior ESCR. **Borstar®FB1200** contains antioxidant.

CAS-No. 25087-34-7

APPLICATIONS

Impact modifier	Grape Cover Films
Greenhouse Films	Monolayer & co-extrusion films
Aquaculture and Pond Liners	Soft Geomembrane
Heavy Duty and Wide Width Film	Mulch Film
Compression Packaging	Industrial Film
Silage Film	

KEY FEATURES

Easy process ability	Excellent draw down
Excellent impact strength – stiffness balance	Toughness at low temperature
Good seal properties	Superior ESCR
Bubble stability	Excellent printability

PHYSICAL PROPERTIES

Property	Typical Value*	Test Method
Density	921 kg/m ³	ASTM D 792
Melt Flow Rate (190°C/2.16kg)	0.17 g/10min	ASTM D1238
Melt Flow Rate (190°C/5.0kg)	0.70 g/10min	ASTM D1238
Melt Flow Rate (190°C/21.6kg)	16 g/10min	ASTM D1238
Melting Temperature	123 °C	ISO 11357/03
Vicat Softening Point A50 (10 N)	100 °C	ISO 306
ESCR – 10% Igepal – F 50%	>5000 Hours	ASTM D1693-B

* Typical properties and data should not be used for specification work

FILM PROPERTIES¹

Property**	Typical Value*	Test Method
Tensile Strength at Break (MD/TD)	62/49 MPa	ISO 527-3
Elongation at Break (MD/TD)	600/770 %	ISO 527-3
Tensile Strength at Yield (TD)	12 MPa	ISO 527-3
Tensile Modulus (1 % Secant) (MD/TD)	250/300 MPa	ASTM D 882
Coefficient of Friction	0.4	ASTM D 1894

Gloss (60°)	10	ASTM D 2457
Dart Drop	1200 g	ASTM D 1709/A
Tear Strength (MD/TD)	4/9 N	ASTM D 1922
Puncture Resistance, force	50 N	ASTM D 5748
Puncture Resistance, energy	3.0 J	ASTM D 5748

¹ Film properties: 40µm, BUR=3:1, FLH=4DD, Die gap 1.2mm

* Typical properties and data should not be used for specification work ** The film properties are dependent on extrusion conditions.

PROCESSING CONDITIONS

Borstar®FB1200 can be processed in most types of blown film equipment such as LDPE, LLDPE or HDPE extruders. The balance of draw down properties and bubble stability is superior to conventional LLDPE and LDPE. Thickness of 10 to >2000mm can be processed with good bubble stability. The product is well suited for co-extrusion.

Recommended extrusion temperature is 190 - 210°C. A die gap of 1.0 - 1.8 mm will give the best balance between extruder pressure and physical properties in the film. Wider die gap gives higher machine direction orientation.

Borstar®FB1200 provides excellent mechanical properties balance by optimizing film processing parameters like Blow up ratio (BUR) and Frost Line Height (FLH). Higher impact strength can be achieved by raising the FLH. High BUR (>2) also results in improved mechanical properties.

Recommended processing conditions:

Melt temperature	190 –220°C
Die gap	1.0 – 1.8 mm
FLH	2 - 4 DD
BUR	>2:1

FOOD CONTACT REGULATIONS

Borstar®FB1200 fulfils the food contact regulations in most countries. If required, contact your Borouge representative for a certificate.

STORAGE

This product should be stored in dry conditions at temperature bellow 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on physical properties of this product.

More information on storage can be found in Safety Information Sheet (SIS) for this product.

SAFETY

The product is not classified as a hazardous mixture.

Dust and fines from the product carry a risk of dust explosion. All equipment should be properly earthed. Inhalation of dust should be avoided as it may cause irritation of the respiratory system. Small amounts of fumes are generated during processing of the product. Proper ventilation is therefore required.

Please see our Safety Information Sheet (SIS) for details on various aspects of safety, recovery and disposal of the product, for more information contact your Borouge representative.

RECYCLING

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

RELATED DOCUMENTS

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

Safety Information Sheet
Statement on chemicals, regulations and standards

STANDARDS

Borouge is certified to various ISO standards, please refer to Borouge.com for more information.

DISCLAIMER

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however, we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borouge makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of Borouge's products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

Borstar® is a trademark of the Borealis group.

Feb 2020