

Polyethylene

Visico™ ME4425 /

Visico™ LE4438

Description

Visico ME4425 / Visico LE4438 is a silane crosslinkable natural compound system designed for insulation of low voltage energy cables. Visico ME4425 is a medium density polyethylene, copolymerized with vinyl silane. Visico LE4438 is a crosslinking catalyst masterbatch specially designed to be used with Visico base resins. The system crosslinks quickly in sauna or in hot water.

Cable insulation with a proper mixture of Visico ME4425 (95 parts) and Visico LE4438 (5 parts) exhibits excellent thermo-oxidative stability. The combination is suitable for both copper and aluminium conductors.

Applications

Visico ME4425 / Visico LE4438 is designed for:

Insulation of low voltage energy cables, range up to 6 kV

Specifications

Visico ME4425 / Visico LE4438 in combination meets the applicable requirements as below when processed using sound extrusion and testing procedure:

ASTM D 1248 Type II, Class A, Category 4
 HD 603 S1
 HD 604 S1
 IEC 60502-1

NEMA WC 70/ ICEA S-100-685
 NEMA WC 71/ ICEA S-96-659
 EN 50290-2-29

The standards referred to above is a selection and is not complete coverage of all applicable standards. Contact your Borealis representative for additional information.

Special Features

Visico ME4425 / Visico LE4438 insulation system offers:

Excellent processing properties
 Low scorch allowing long runs and more frequent tooling changes
 Excellent surface finish


Less smell, more consistent quality (no volatiles)
 Good curing speed
 No drying prior to extrusion
 Excellent storage stability

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density (mixture 95:5)	930 kg/m ³	ISO 1183-1, Method A
Melt Flow Rate (190 °C/2,16 kg)	1,0 g/10min	ISO 1133
Tensile Strain at Break (250 mm/min)	> 300 %	IEC 60811-501
Tensile Strength (250 mm/min)	> 20 MPa	IEC 60811-501
Change of Tensile Properties After Ageing (240 h, 135 °C) 1	<= 25 %	IEC 60811-401
Brittleness temperature	< -76 °C	ASTM D 746

Visico is a trademark of the Borealis group.

Borealis AG | Wagramer Strasse 17-19 | 1220 Vienna | Austria
 Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
 FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com



Polyethylene

Visico ME4425 / Visico LE4438

Environmental Stress Crack Resistance (50 °C, Igepal 10 % %, F20)	> 96 h	IEC 60811-406
Hardness, Shore D (1 s)	55	ISO 868
Hot Set Test (200 °C, 0,20 MPa)	Elongation under load Permanent deformation	60 % 0 %
		IEC 60811-507

¹ These values are based on sufficient crosslinked/cured Visico. If Visico is not sufficiently crosslinked the material will continue to crosslink during the ageing procedure and a larger change between values before and after ageing may occur.

Electrical Properties

Property	Typical Value	Test Method
	Data should not be used for specification work	
Dielectric constant (50 Hz)	< 2,3	IEC 60250
DC Volume Resistivity	> 10 PΩcm	IEC 60093
Dielectric Strength	> 22 kV/mm	IEC 60243

Processing Techniques

Visico ME4425 / Visico LE4438 are suitable for most equipment designed for PVC/PE extrusion.

Extrusion

Typically the following process conditions are used:

Barrel 1	150 °C
Barrel 2	185 °C
Barrel 3	185 °C
Barrel 4	185 °C
Die head	185 °C
Melt temperature	190 - 195 °C

The temperature of the melted polymer during extrusion should preferably not exceed 200 °C. Having the above set temperature profile, a stable extrusion process and a cable having smooth glossy appearance should be achieved. On-size pressure or draw down tube-on tooling is preferred. The use of a gradient cooling bath will improve the cable insulation physical properties further.

Conductor preheating up to 100°C is recommended when producing cables with a conductor up to 16 mm² for good mechanical properties.

Crosslinking

These products can be crosslinked by immersion in hot water or exposed to low pressure steam at a temperature up to 90°C. This time period may be varied due to the humidity, thickness of insulation, reel size and temperature.

Example: Visico ME4425/Visico LE4438. Time to reach Hot Set elongation value of 100%.

Thickness	Time
------------------	-------------



Polyethylene

Visico ME4425 / Visico LE4438

0,7 mm

2 h

90°C, Sauna or water bath.

Packaging

Visico ME4425 - Base material is protected from moisture ingress

Package: Octabins
Bulk

Visico LE4438 - Catalyst master batch is protected from moisture ingress

Package: Bags
Smallbins

Storage

Visico ME4425 / Visico LE4438 has excellent storage stability. Visico ME4425 and Visico LE4438 can be stored for 18 months after production, at 10-30°C (50-85°F) in unopened original packages, without significant deterioration in the quality of the material. Visico ME4425 and Visico LE4438 should be stored in dry conditions and protected from direct sunlight. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product. Visico LE4438 is sensitive to moisture and is therefore delivered with low moisture content, ready to be used. Pre-drying is not recommended, as it will destroy the drying agent that has been added to prevent the material to take up moisture. The bags must be properly resealed between uses, as even short periods of storage in humid conditions may cause scorch during extrusion.

Safety

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.